Shield Lubricants & Specialities Pvt. Ltd.

LABORATORY TEST REPORT

PRODUCT NAME : SHIELD MFL 68	DATE : 22/03/17
BATCH NO : SL/17-03/621	

SR. NO.	TEST PARAMETER	TEST METHOD	CUSTOMER SPECIFICATION		BATCH RESULT
			MINIMUM	MAXIMUM	
1	Appearance	Visual	Clear & Bright		Cl. & Br.
2	Crackle Test	In-House	NIL		Nil
3	Colour	ASTM D-1500	2.5 MAX		L 2.0
4	Density @29.5°C	ASTM D-1298	To Be reported		0.8738
5	Kin Visc.@40°C	ASTM D-445	64	72	65.62
6	Kin Visc.@100°C	ASTM D-445	To Be reported		8.42
7	Viscosity Index	ASTM D-2270	90 Minimum		97
8	Flash Point, °C, COC	ASTM D-92	210(T)		240
9	Pour Point, °C	ASTM D-97	-6 Maximum		-6

Tested By: Sandip

Regd. Office: Commodity Exchange Bldg, 5th floor, Office no.522,Plot No. 2,3 & 4, Sector-19, Vashi, Navi-Mumbai : 400705, Maharastra, INDIA.
L: 022-27832855 Fax : 022-27832855
Website : www.shieldlubricants.com