



**Shield Lubricants & Specialities Pvt. Ltd.**

## LABORATORY TEST REPORT

PRODUCT NAME : SHIELD TURBOXTRA 15W40	DATE : 24/04/17
BATCH NO : SL/17-04/50	

SR. NO.	TEST PARAMETER	TEST METHOD	CUSTOMER SPECIFICATION		BATCH RESULT
			MINIMUM	MAXIMUM	
1	Appearance	Visual	Clear & Bright		Cl. & Br.
2	Crackle Test	In-House	NIL		Nil
3	Colour	ASTM D-1500	Match with Standard		L 3.0
4	Density @29.5°C	ASTM D-1298	To Be reported		0.8755
5	Kin Visc.@100°C	ASTM D-445	14	15.5	14.75
6	Kin Visc.@40°C	ASTM D-445	To Be reported		112.1
7	Viscosity Index	ASTM D-2270	130 Minimum		135
8	Flash Point, °C, COC	ASTM D-92	220(T)		228
9	Pour Point, °C	ASTM D-97	-24 Maximum		-24
10	TBN, mg of KOH/gm	ASTM D-2896	9 Minimum		9.63

Tested By: *Sandip*