



Shield Lubricants & Specialities Pvt. Ltd.

LABORATORY TEST REPORT

PRODUCT NAME : SHIELD GPO 32	DATE : 25/04/17
BATCH NO : SL/17-04/54	

SR. NO.	TEST PARAMETER	TEST METHOD	CUSTOMER SPECIFICATION		BATCH RESULT
			MINIMUM	MAXIMUM	
1	Appearance	Visual	Clear & Bright		Cl. & Br.
2	Crackle Test	In-House	NIL		Nil
3	Colour	ASTM D-1500	L 0.5 MAX		W.W
4	Density @29.5°C	ASTM D-1298	To Be reported		0.8380
5	Kin Visc.@40°C	ASTM D-445	28	32	28.86
6	Kin Visc.@100°C	ASTM D-445	To Be reported		5.28
7	Viscosity Index	ASTM D-2270	95 Minimum		116
8	Flash Point, °C, COC	ASTM D-92	190(T)		218
9	Pour Point, °C	ASTM D-97	-18 Maximum		<-9

Tested By: *Sandip*