



**Shield Lubricants & Specialities Pvt. Ltd.**

## LABORATORY TEST REPORT

PRODUCT NAME : PETROASIA TRANS GEAR EP 80W90 GL-4	DATE : 03/05/17
BATCH NO : SL/17-05/71	

SR. NO.	TEST PARAMETER	TEST METHOD	CUSTOMER SPECIFICATION		BATCH RESULT
			MINIMUM	MAXIMUM	
1	Appearance	Visual	Clear & Bright		Cl. & Br.
2	Crackle Test	In-House	NIL		Nil
3	Colour	ASTM D-1500	4.0 MAX		L 3.5
4	Density @29.5°C	ASTM D-1298	To Be reported		0.8833
5	Kin Visc.@100°C	ASTM D-445	14	15.5	15.24
6	Kin Visc.@40°C	ASTM D-445	To Be reported		146.9
7	Viscosity Index	ASTM D-2270	94 Minimum		105
8	Flash Point, °C, COC	ASTM D-92	210(T)		232
9	Pour Point, °C	ASTM D-97	-21 Maximum		-21
10	TAN, mg of KOH/gm	ASTM D-974	0.25 Minimum		0.85

Tested By: *Sandip*