



Shield Lubricants & Specialities Pvt. Ltd.

LABORATORY TEST REPORT

PRODUCT NAME : SHIELD TURBOXTRA 15W40	DATE : 27/07/17
BATCH NO : SL/17-07/235	

SR. NO.	TEST PARAMETER	TEST METHOD	CUSTOMER SPECIFICATION		BATCH RESULT
			MINIMUM	MAXIMUM	
1	Appearance	Visual	Clear & Bright		Cl. & Br.
2	Crackle Test	In-House	NIL		Nil
3	Colour	ASTM D-1500	Match with Standard		L 3.5
4	Density @29.5°C	ASTM D-1298	To Be reported		0.8723
5	Kin Visc.@100°C	ASTM D-445	14	15.5	14.82
6	Kin Visc.@40°C	ASTM D-445	To Be reported		115.2
7	Viscosity Index	ASTM D-2270	130 Minimum		132
8	Flash Point, °C, COC	ASTM D-92	220(T)		226
9	Pour Point, °C	ASTM D-97	-24 Maximum		-24
10	TBN, mg of KOH/gm	ASTM D-2896	9 Minimum		9.95

Tested By: *Sandip*