



LABORATORY TEST REPORT

PRODUCT NAME :SHIELD ULTRA CUT	DATE : 18/04/2022
BATCH NO. : SL/22-04/116	LAB.SR.NO. – 051

SR. NO.	TEST	TEST METHOD	UNIT	SPECIFICATION	BATCH TEST REPORT
1	Appearance	Visual	Clear & Bright	Clear & Bright
2	Colour	ASTM D-1500	Dark Brown	Brown
3	Density @29.5°C	ASTM D-1298	Kg/L	Reported	0.8850
4	Kin. Visc.@40°C	ASTM D-445	cST	45.00 Min. - 60.00 Max.	52.15
5	5% Emulsion In 500 ppm Hard Water	IS- 1115	Stable With Out Any Separation For 24 Hrs. Min.	Pass
6	5% Emulsion In Tap Water	IS- 1115	Stable With Out Any Separation For 24 Hrs. Min.	Pass
7	Thermal Stability (cold & hot)	IS- 1115	°C	Shall Pass The Test	Pass
8	TAN, mg of KOH/gm	ASTM D-2896	mg of KOH/gm	5 Max.	3.26
9	Cu Corrosion,@100°C	ASTM D-130	°C	1a Max.	1a Pass
10	PH@5% Distilled	ASTM D1287	---	9 PH Min.	9.20

REMARK: SAMPLE PASS

PREPARED BY: ANIL JARHAD

APPROVED BY: SANDIP BHAYAJE