



Shield Lubricants & Specialities Pvt. Ltd.

LABORATORY TEST REPORT

PRODUCT NAME : SESTINA GEAR EP 320 ISO VG 320	DATE : 03/01/2024
BATCH NO. : SL/24-01/3666	LAB.SR.NO. – 3002

SR. NO.	TEST	TEST METHOD	UNIT	SPECIFICATION	BATCH TEST REPORT
1	Appearance	Visual	Clear & Bright	Clear & Bright
2	Crackle Test	Visual	Nil	Nil
3	Colour	ASTM D-1500	L4.0 Max.	L1.5
4	Density @29.5°C	ASTM D-1298	Kg/ml	Report	0.8803
5	Kinematic Viscosity @ 40°C	ASTM D-445	cSt	305 Min. - 330 Max.	316.0
6	Kinematic Viscosity @ 100°C	ASTM D-445	cSt	Report	27.19
7	Viscosity Index	ASTM D-2270	90 Min.	115
8	Total Acid Number	ASTM D-974	MgKOH/gm	Report	0.27
9	Flash Point ,COC	ASTM D-92	°C	210 Min.	226
10	Pour Point	ASTM D-97	°C	-3 Min.	-9

REMARK: SAMPLE PASS

TESTED BY: ANIL JARHAD

APPROVED BY: SANDIP BHAYAJE

Regd.Office: Shelton Sapphire, 8TH Floor, 806-B, Plot No: 18-19, Sector-15,
CBD Belapur, Navi Mumbai-400614, Maharashtra. India.
L—022-27582828, Website-www.shieldlubricants.com