



Shield Lubricants & Specialities Pvt. Ltd.

LABORATORY TEST REPORT

PRODUCT NAME:SHIELD SESTINA GEAR EP 100 ISO VG 100	DATE : 21/11/2024
BATCH NO: SL/24-11/1390	LAB.SR.NO. -941

SR.NO	TEST	TEST METHOD	UNIT	SPECIFICATION	BATCH TEST REPORT
1	Appearance	Visual	Clear & Bright	Clear & Bright
2	Crackle test	----	Nil	Nil
3	Density @ 29.5°C	ASTM D 1298	Kg/ml	Report	0.8783
4	Colour	ASTM D 1500	L2.5 Max.	L2.0
5	Kinematic Viscosity @ 40°C	ASTM D 445	cSt	90 Min. - 110 Max.	91.77
6	Kinematic Viscosity @ 100°C	ASTM D 445	cSt	Report	11.36
7	Viscosity Index	ASTM D2270	90 Min.	111
8	Pour Point	ASTM D97	°C	-3 Max.	-6
9	Flash Point , COC	ASTM D92	°C	210 Min.	228
10	Total Acid Number	ASTM D974	MgKOH/gm	1 Max.	0.56

REMARK: SAMPLE PASS

TESTED BY: ANIL JARHAD

APPROVED BY: SANDIP BHAYAJE

DISCLAIMER: THIS IS A COMPUTER-GENERATED REPORT AND DOES NOT REQUIRE A PHYSICAL SIGNATURE.

Regd.Office: Shelton Sapphire, 8TH Floor, 806-B, Plot No: 18-19, Sector-15,
CBD Belapur, Navi Mumbai-400614, Maharashtra. India.
L—022-27582828, Website-www.shieldlubricants.com