



Shield Lubricants & Specialities Pvt. Ltd.

LABORATORY TEST REPORT

PRODUCT NAME :SHIELD FERRO M 5000	DATE : 24/12/2024
BATCH NO : SL/24-12/1635	LAB.SR.NO. – 1094

SR. NO.	TEST	TEST METHOD	UNIT	SPECIFICATION		BATCH TEST REPORT
				MIN.	MAX.	
1	Appearance	Visual	Clear & Bright		Clear & Bright
2	Colour	ASTM D-1500	Dark Brown		Dark Brown
3	Density @29.5°C	ASTM D-1298	Kg/ml	Report		0.9223
4	KV@40°C	ASTM D445	cST	Report		94.39
5	5% Emulsion In 500 ppm Hard Water	IS- 1115	Stable With Out Any Separation For 24 Hrs Min		Pass
6	5% Emulsion In 200 ppm Hard Water	IS- 1115	Stable With Out Any Separation For 24 Hrs Min		Pass
7	Thermal Stability (cold & hot)	IS- 1115	°C	Shall Pass The Test		Pass
8	Emulsion Type	Translucent		Translucent pass
9	PH Test	9 PH Min.		9.58
10	Cu Corrosion, @100°C	ASTM D-130	°C	Report		1a Pass
11	TAN, mg of KOH/gm	ASTM D974	MgKOH/gm	Report		8.42
12	Fungus Odor Test	Report		Ok

REMARK – SAMPLE PASS

TESTED BY: ANIL JARHAD

APPROVED BY: SANDIP BHAYAJE

DISCLAIMER: THIS IS A COMPUTER-GENERATED REPORT AND DOES NOT REQUIRE A PHYSICAL SIGNATURE.

Regd.Office: Shelton Sapphire, 8TH Floor, 806-B, Plot No: 18-19, Sector-15,
CBD Belapur, Navi Mumbai-400614, Maharashtra. India.
L—022-27582828, Website-www.shieldlubricants.com