



LABORATORY TEST REPORT

PRODUCT NAME :SHIELD SESTINA GEAR EP 460 ISO VG 460	DATE : 13/01/2025
BATCH NO : SL/25-01/1722	LAB.SR. NO: 1188

SR. NO.	TEST	TEST METHOD	UNIT	SPECIFICATION	BATCH TEST REPORT
1	Appearance	Visual	Clear & Bright	Clear & Bright
2	Crackle Test	Visual	Nil	Nil
3	Colour	ASTM D-1500	L4.0 Max.	L2.0
4	Density @29.5°C	ASTM D-1298	Kg/ml	Report	0.8933
5	Kinematic Viscosity @ 40°C	ASTM D-445	cSt	410 - 430	417.0
6	Kinematic Viscosity @ 100°C	ASTM D-445	cSt	Report	31.20
7	Viscosity Index	ASTM D-2270	90 Min.	106
8	TAN, mg of KOH/gm	ASTM D-974	mg of KOH/gm	1 Max.	0.48
9	Flash Point, COC	ASTM D-92	°C	220 Min.	238
10	Pour Point	ASTM D-97	°C	-3 Max.	-6

REMARK: SAMPLE PASS

PREPARED BY: ANIL JARHAD

APPROVED BY: SANDIP BHAYAJE

DISCLAIMER: THIS IS A COMPUTER-GENERATED REPORT AND DOES NOT REQUIRE A PHYSICAL SIGNATURE.