



LABORATORY TEST REPORT

PRODUCT NAME:SHIELD SESTINA GEAR EP 68 ISO VG 68	DATE : 25/01/2025
BATCH NO : SL/25-01/1776	LAB.SR.NO. – 1240

SR.NO	TEST	TEST METHOD	UNIT	SPECIFICATION	BATCH TEST REPORT
1	Appearance	Visual	Clear & Bright	Clear & Bright
2	Crackle test	Visual	Nil	Nil
3	Density @ 29.5°C	ASTM D 1298	Kg/ml	Report	0.8446
4	Colour	ASTM D 1500	L2.5 Max.	L1.5
5	Kinematic Viscosity @ 40°C	ASTM D 445	cSt	61.2 Min. - 74.8 Max.	63.01
6	Kinematic Viscosity @ 100°C	ASTM D 445	cSt	Report	10.58
7	Viscosity Index	ASTM D2270	90 Min.	158
8	Pour Point	ASTM D97	°c	-3 Max.	-15
9	Flash Point ,COC	ASTM D92	°c	200 Min.	210
10	Total Acid Number	ASTM D974	MgKoh/gm	1 Max.	0.61

REMARK: SAMPLE PASS

PREPARED BY: ANIL JARHAD

APPROVED BY: SANDIP BHAYAJE

DISCLAIMER: THIS IS A COMPUTER-GENERATED REPORT AND DOES NOT REQUIRE A PHYSICAL SIGNATURE.

Regd.Office: Shelton Sapphire, 8TH Floor, 806-B, Plot No: 18-19, Sector-15,
CBD Belapur, Navi Mumbai-400614, Maharashtra. India.
L—022-27582828, Website-www.shieldlubricants.com