



**LABORATORY TEST REPORT**

PRODUCT NAME: MFL 68	DATE : 06/05/2025
BATCH NO : SL/25-05/207	LAB.SR.NO. – 134

SR.NO	TEST	TEST METHOD	UNIT	SPECIFICATION	BATCH TEST REPORT
1	Appearance	Visual	....	Clear & Bright	Clear & Bright
2	Crackle test	Visual	....	Nil	Nil
3	Density @ 29.5°C	ASTM D 1298	Kg/ml	Report	0.8704
4	Colour	ASTM D 1500	....	L2.5 Max.	L2.0
5	Kinematic Viscosity @ 40°C	ASTM D 445	cSt	61.2 Min. - 74.8 Max.	66.23
6	Kinematic Viscosity @ 100°C	ASTM D 445	cSt	Report	10.50
7	Viscosity Index	ASTM D2270	....	90 Min.	146
8	Pour Point	ASTM D97	°c	-3 Min.	-12
9	Flash Point ,COC	ASTM D92	°c	210 Min.	212

REMARK: SAMPLE PASS

PREPARED BY: ANIL JARHAD

APPROVED BY : SANDIP BHAYAJE

DISCLAIMER: THIS IS A COMPUTER-GENERATED REPORT AND DOES NOT REQUIRE A PHYSICAL SIGNATURE.

Regd.Office: Shelton Sapphire, 8TH Floor, 806-B, Plot No: 18-19, Sector-15,  
CBD Belapur, Navi Mumbai-400614, Maharashtra. India.  
L—022-27582828, Website-www.shieldlubricants.com