



Shield Lubricants & Specialities Pvt. Ltd.

LABORATORY TEST REPORT

PRODUCT NAME : FERRO M 500	DATE : 30/06/2025
BATCH NO : SL/25-06/587	LAB.SR.NO. – 376

SR. NO.	TEST	TEST METHOD	UNIT	SPECIFICATION		BATCH TEST REPORT
				MINIMUM	MAXIMUM	
1	Appearance	Visual	Clear & Bright		Clear & Bright
2	Colour	ASTM D-1500	Amber		Amber
3	Density @29.5°C	ASTM D-1298	Kg/ml	report		0.9885
4	Kinematic Viscosity @ 40°C	ASTM D 445	cST	Report.		83.02
5	5% Emulsion In 500 ppm Hard Water	IS- 1115	Stable With Out Any Separation For 24 Hrs. Min.		Pass
6	5% Emulsion In 200 ppm Hard Water	IS- 1115	Stable With Out Any Separation For 24 Hrs. Min.		Pass
7	Thermal Stability (cold & hot)	IS- 1115	°C	Shall Pass The Test		Pass
8	Emulsion Type		Translucent		Translucent pass
9	De Foam test @5% in 50ppm		Nil after 14 sec.
10	PH Test		9 PH Min.		9.68

REMARK – SAMPLE PASS

PREPARED BY: ANIL JARHAD

APPROVED BY: SANDIP BHAYAJE

DISCLAIMER: THIS IS A COMPUTER-GENERATED REPORT AND DOES NOT REQUIRE A PHYSICAL SIGNATURE.

Regd.Office: Shelton Sapphire, 8TH Floor, 806-B, Plot No: 18-19, Sector-15,
CBD Belapur, Navi Mumbai-400614, Maharashtra. India.
L—022-27582828, Website-www.shieldlubricants.com