



**LABORATORY TEST REPORT**

PRODUCT NAME :SHIELD MFL 460 ISO 460	DATE :23/07/2025
BATCH. NO : SL/25-07/735	LAB.SR.NO. – 481

SR. NO.	TEST	TEST METHOD	UNIT	SPECIFICATION	BATCH TEST REPORT
1	Appearance	Visual	....	Clear & Bright	Clear & Bright
2	Crackle Test	Visual	....	Nil	Nil
3	Colour	ASTM D-1500	....	L4.0 Max.	L1.0
4	Density @29.5°C	ASTM D-1298	Kg/ml	Report	0.8590
5	Kinematic Viscosity @ 40°C	ASTM D-445	cSt	430 Min. - 460 Max.	459.0
6	Kinematic Viscosity @ 100°C	ASTM D-445	cSt	Report	55.99
7	Viscosity Index	ASTM D-2270	....	90 Min.	190
8	Flash Point , COC	ASTM D-92	°C	200 Min.	214
9	Pour Point	ASTM D-97	°C	-3 Max.	-15

REMARK – SAMPLE PASS

TESTED BY: ANIL JARHAD

APPROVED BY: SANDIP BHAYAJE

DISCLAIMER: THIS IS A COMPUTER-GENERATED REPORT AND DOES NOT REQUIRE A PHYSICAL SIGNATURE.