



**LABORATORY TEST REPORT**

PRODUCT NAME:SHIELD SESTINA GEAR EP 68 ISO VG 68	DATE : 07/08/2025
BATCH NO: SL/25-08/861	LAB.SR.NO. – 547

SR.NO	TEST	TEST METHOD	UNIT	SPECIFICATION	BATCH TEST REPORT
1	Appearance	Visual	....	Clear & Bright	Clear & Bright
2	Crackle test	----	....	Nil	Nil
3	Density @ 29.5°C	ASTM D 1298	Kg/ml	Report	0.8669
4	Colour	ASTM D 1500	....	L2.5 Max.	L1.5
5	Kinematic Viscosity @ 40°C	ASTM D 445	cSt	61.2 Min. – 74.8 Max.	70.74
6	Kinematic Viscosity @ 100°C	ASTM D 445	cSt	Report	11.15
7	Viscosity Index	ASTM D2270	....	90 Min.	144
8	Pour Point	ASTM D97	°C	-3 Max.	-15
9	Flash Point , COC	ASTM D92	°C	210 Min.	204
10	Total Acid Number	ASTM D974	MgKOH/gm	1 Max.	0.86

REMARK: SAMPLE PASS

PREPARED BY: ANIL JARHAD

APPROVED BY: SANDIP BHAYAJE

DISCLAIMER: THIS IS A COMPUTER-GENERATED REPORT AND DOES NOT REQUIRE A PHYSICAL SIGNATURE.