



**Shield Lubricants & Specialities Pvt. Ltd.**

## LABORATORY TEST REPORT

|                            |                   |
|----------------------------|-------------------|
| PRODUCT NAME: RUSTIC DW 32 | DATE : 12/08/2025 |
| BATCH NO: SL/25-08/883     | LAB.SR.NO. – 561  |

| SR.NO | TEST                       | TEST METHOD    | UNIT  | SPECIFICATION       | BATCH TEST REPORT |
|-------|----------------------------|----------------|-------|---------------------|-------------------|
| 1     | Appearance                 | Visual         | -     | Clear & Bright      | Clear & Bright    |
| 2     | Density @ 29.5°C           | ASTM D 1298    | Kg/ml | Reported            | 0.7908            |
| 3     | Colour                     | ASTM D 1500    | ....  | L3.0 Max.           | L2.0              |
| 4     | Kinematic Viscosity @ 40°C | ASTM D 445     | cSt   | 1.3 Min. - 3.5 Max. | 1.47              |
| 5     | Flash Point PMCC.          | ASTM D-91      | °C    | 40 Min.             | 58                |
| 6     | Water Displacement Test    | ....           | ....  | ....                | Pass              |
| 7     | Cu Corrosion Test@100°C    | ASTM D130      | °C    | 1A Pass             | 1A pass           |
| 8     | Salt Spray Test            | ASTM B117-2003 | Hrs.  | 20 Min. - 30 Max.   | 26                |

REMARK: SAMPLE PASS

TESTED BY: ANIL JARHAD

APPROVED BY: SANDIP BHAYAJE

DISCLAIMER: THIS IS A COMPUTER-GENERATED REPORT AND DOES NOT REQUIRE A PHYSICAL SIGNATURE.

Regd.Office: Shelton Sapphire, 8TH Floor, 806-B, Plot No: 18-19, Sector-15,  
CBD Belapur, Navi Mumbai-400614, Maharashtra. India.  
L—022-27582828, Website-www.shieldlubricants.com