

### LABORATORY TEST REPORT

<b>PRODUCT.NAME:SHIELD RUSTIC OB 631</b>	<b>DATE :18/08/2025</b>
<b>BATCH. NO: SL/25-08/929</b>	<b>LAB.SR.NO. – 391</b>

SR.NO	TEST	TEST METHOD	UNIT	SPECIFICATION		BATCH TEST REPORT
				Min.	Max.	
1	Appearance	Visual	....	Clear & Bright		Clear & Bright
2	Crackle Test	Visual	....	NIL		Nil
3	Density @ 29.5°C	ASTM D 1298	Kg/ml	Reported		0.8184
4	Colour D	ASTM D 1500	....		L2.5	L0.0
5	Kinematic Viscosity @ 100°C	ASTM D 445	cSt	Reported		3.10
6	Kinematic Viscosity @ 40°C	ASTM D 445	cSt	9	14	12.28
7	Viscosity Index	ASTM D 2270	....	100		112
8	Flash Point, COC	ASTM D92	°C	150		196
9	Pour Point	ASTM D97	°C		-3	-30

REMARK – SAMPLE PASS

TESTED BY: ANIL JARHAD

APPROVED BY: SANDIP BHAYAJE

**DISCLAIMER: THIS IS A COMPUTER-GENERATED REPORT AND DOES NOT REQUIRE A PHYSICAL SIGNATURE**