



LABORATORY TEST REPORT

PRODUCT NAME: SHIELD WARRIOR HLP 68	DATE : 21/08/2025
BATCH. NO: SL/25-08/961	LAB.SR.NO. – 614

SR.NO	TEST	TEST METHOD	UNIT	SPECIFICATION	BATCH TEST REPORT
1	Appearance	Visual	Clear & Bright	Clear & Bright
2	Crackle test	Visual	Nil	Nil
3	Density @ 29.5°C	ASTM D 1298	Kg/ml	Report	0.8572
4	Colour	ASTM D 1500	L2.5 Max.	L0.5
5	Kinematic Viscosity @ 40°C	ASTM D 445	cSt	61.2 Min. - 74.8 Max.	65.49
6	Kinematic Viscosity @ 100°C	ASTM D 445	cSt	Report	9.32
7	Viscosity Index	ASTM D2270	90 Min.	120
8	Foaming, Tendency/Stability.	ASTM D 892			
	Sequence I at 24±0.5°C		ml	150/0 Max.	10/0
	Sequence II at 93.5±0.5°C		ml	75/0 Max.	20/0
	Sequence III at 24±0.5°C		ml	150/0 Max.	10/0
9	Demulsibility @ 54°C±1°C	ASTM D1401	minutes	40 – 37-3 (30) Max.	40-40-0(20)
10	Tan	ASTM D974	MgKOH/g	1 Max.	0.88
11	Flash Point, COC	ASTM D92	°C	210 Min.	216
12	Pour Point	ASTM D-97	°C	-15 Min.	- 24

REMARK : SAMPLE PASS

TESTED BY : ANIL JARHAD

APPROVED BY: SANDIP BHAYAJE

SIGNATURE DISCLAIMER: THIS IS A COMPUTER-GENERATED REPORT AND DOES NOT REQUIRE A PHYSICAL