



LABORATORY TEST REPORT

PRODUCT NAME:SHIELD MFL 68 ISO VG 68	DATE : 31/08/2025
BATCH NO : SL/25-08/989	LAB.SR.NO. – 623

SR.NO	TEST	TEST METHOD	UNIT	SPECIFICATION	BATCH TEST REPORT
1	Appearance	Visual	Clear & Bright	Clear & Bright
2	Crackle test	Visual	Nil	Nil
3	Density @ 29.5°C	ASTM D 1298	Kg/ml	Reported	0.8656
4	Colour	ASTM D 1500	L2.5 Max.	L1.0
5	Kinematic Viscosity @ 40°C	ASTM D 445	cSt	61.2 Min. - 74.8 Max.	68.81
6	Kinematic Viscosity @ 100°C	ASTM D 445	cSt	Reported	10.72
7	Viscosity Index	ASTM D2270	90 Min.	145
8	Pour Point	ASTM D97	°C	-3 Min.	-12
9	Flash Point ,COC	ASTM D92	°C	210 Min.	210

REMARK: SAMPLE PASS

TESTED BY: ANIL JARHAD

APPROVED BY : SANDIP BHAYAJE

DISCLAIMER: THIS IS A COMPUTER-GENERATED REPORT AND DOES NOT REQUIRE A PHYSICAL SIGNATURE.

Regd.Office: Shelton Sapphire, 8TH Floor, 806-B, Plot No: 18-19, Sector-15,
CBD Belapur, Navi Mumbai-400614, Maharashtra. India.
L—022-27582828, Website-www.shieldlubricants.com