



**LABORATORY TEST REPORT**

PRODUCT NAME: DURA COMRESSOR VDL T 68	DATE : 14/09/2025
BATCH. NO: SL/25-09/1121	LAB.SR.NO. – 715

SR.NO	TEST	TEST METHOD	UNIT	SPECIFICATION	BATCH TEST REPORT
1	Appearance	Visual	.....	Clear & Bright	Clear & Bright
2	Crackle test	Visual	.....	Nil	Nil
3	Density @ 29.5°C	ASTM D 1298	Kg/ml	Report	0.8583
4	Colour	ASTM D 1500	.....	L2.5 Max.	L0.5
5	Kinematic Viscosity @ 40°C	ASTM D 445	cSt	61.2 Min. - 74.8 Max.	63.28
6	Kinematic Viscosity @ 100°C	ASTM D 445	cSt	Report	8.90
7	Viscosity Index	ASTM D2270	.....	95 Min.	115
8	Foaming, Tendency/Stability.	ASTM D 892			
	Sequence I at 24±0.5°C		ml	150/0 Max.	10/0
	Sequence II at 93.5±0.5°C		ml	75/0 Max.	10/0
	Sequence III at 24±0.5°C		ml	150/0 Max.	10/0
9	Demulsibility @ 54°C±1°C	ASTM D1401	minutes	40 – 37-3 (30) Max.	40-40-0(20)
10	Tan	ASTM D974	MgKOH/g	1 Max.	0.95
11	Flash Point, COC	ASTM D92	°C	210 Min.	228
12	Pour Point	ASTM D-97	°C	-15 Min.	- 24

REMARK: SAMPLE PASS

PREPARED BY: ANIL JARHAD

APPROVED BY: SANDIP BHAYAJE

DISCLAIMER: THIS IS A COMPUTER-GENERATED REPORT AND DOES NOT REQUIRE A PHYSICAL SIGNATURE.

Regd.Office: Shelton Sapphire, 8TH Floor, 806-B, Plot No: 18-19, Sector-15,  
CBD Belapur, Navi Mumbai-400614, Maharashtra. India.  
L—022-27582828, Website-www.shieldlubricants.com