



LABORATORY TEST REPORT

PRODUCT NAME : SHIELD SESTINA GEAR XTREME LOAD	DATE : 27/09/2025
BATCH NO : SL/25-09/1207	LAB.SR.NO. – 779

SR. NO.	TEST	TEST METHOD	UNIT	SPECIFICATION		BATCH TEST REPORT
				MINIMUM	MAXIMUM	
1	Appearance	Visual	Clear & Bright		Clear & Bright
2	Crackle Test	Visual	Nil		Nil
3	Colour	ASTM D-1500	L4.0 Max.		L3.0
4	Density @29.5°C	ASTM D-1298	Kg/ml	Report		0.8991
5	Kin Visc. @100°C	ASTM D-445	cSt	Report		43.13
6	Kin Visc. @40°C	ASTM D-445	cSt	630 Min. – 680 Max.		647.0
7	Viscosity Index	ASTM D-2270	Report		110
8	TAN, mg of KOH/gm	ASTM D-974	mg of KOH/gm		1	0.43
9	Flash Point ,COC	ASTM D-92	°C	220		256
10	Pour Point	ASTM D-97	°C		-3	-6

REMARK: SAMPLE PASS

PREPARED BY: ANIL JARHAD

APPROVED BY: SANDIP BHAYAJE

DISCLAIMER: THIS IS A COMPUTER-GENERATED REPORT AND DOES NOT REQUIRE A PHYSICAL SIGNATURE.