



Shield Lubricants & Specialities Pvt. Ltd.

LABORATORY TEST REPORT

| | |
|------------------------------|-------------------|
| PRODUCT NAME: PRO TRANS UTTO | DATE : 28/01/2026 |
| BATCH NO: SL/26-01/2062 | LAB.SR.NO. – 1349 |

| SR.NO | TEST | TEST METHOD | UNIT | SPECIFICATION | BATCH TEST REPORT |
|-------|-----------------------------|-------------|----------|-------------------------|-------------------|
| 1 | Appearance | Visual | | Clear & Bright | Clear & Bright |
| 2 | Crackle test | ---- | | Nil | Nil |
| 3 | Density @ 29.5°C | ASTM D 1298 | Kg/ml | Report | 0.8642 |
| 4 | Colour | ASTM D 1500 | | L2.5 Max. | L1.5 |
| 5 | Kinematic Viscosity @ 40°C | ASTM D 445 | cSt | Report | 95.92 |
| 6 | Kinematic Viscosity @ 100°C | ASTM D 445 | cSt | 10.50 Min. - 12.50 Max. | 11.02 |
| 7 | Viscosity Index | ASTM D2270 | | 90 | 99 |
| 8 | Pour Point | ASTM D97 | °C | -21 Max. | -24 |
| 9 | Flash Point , COC | ASTM D92 | °C | 210 Min. | 232 |
| 10 | Total Acid Number | ASTM D974 | MgKOH/gm | 1 Max. | 0.62 |

REMARK: SAMPLE PASS

PREPARED BY: ANIL JARHAD

APPROVED BY: SANDIP BHAYAJE

DISCLAIMER: THIS IS A COMPUTER-GENERATED REPORT AND DOES NOT REQUIRE A PHYSICAL SIGNATURE.

Regd.Office: Shelton Sapphire, 8TH Floor, 806-B, Plot No: 18-19, Sector-15,
CBD Belapur, Navi Mumbai-400614, Maharashtra. India.
L—022-27582828, Website-www.shieldlubricants.com