



**Shield Lubricants & Specialities Pvt. Ltd.**

**LABORATORY TEST REPORT**

|  |                   |
|--|-------------------|
| PRODUCT NAME :SHIELD PERFORMANCE 4T 20W40 API SL | DATE : 23/02/2026 |
| BATCH NO : SL/26-02/2298                         | LAB.SR.NO. – 1475 |

| SR. NO. | TEST                        | TEST METHOD | UNIT         | SPECIFICATION           | BATCH TEST REPORT |
|---------|-----------------------------|-------------|--------------|-------------------------|-------------------|
| 1       | Appearance                  | Visual      | ....         | Clear & Bright          | Clear & Bright    |
| 2       | Crackle Test                | Visual      | ....         | Nil                     | Nil               |
| 3       | Colour                      | ASTM D-1500 | ....         | Red                     | Red               |
| 4       | Density @29.5°C             | ASTM D-1298 | Kg/ml        | Report                  | 0.8790            |
| 5       | Kinematic Viscosity @ 100°C | ASTM D-445  | cSt          | 14.00 Min. - 15.50 Max. | 14.95             |
| 6       | Kinematic Viscosity @ 40°C  | ASTM D-445  | cSt          | Report                  | 137.0             |
| 7       | Viscosity Index             | ASTM D-2270 | ....         | 110 Min.                | 110               |
| 8       | TBN, mg of KOH/gm           | ASTM D-2896 | mg of KOH/gm | 6.00 Min.               | 6.81              |
| 9       | Pour Point                  | ASTM D97    | °C           | -24 Max.                | -27               |
| 10      | Flash Point, COC            | ASTM D92    | °C           | 210 Min.                | 228               |

REMARK – SAMPLE PASS

TESTED BY: ANIL JARHAD

APPROVED BY: SANDIP BHAYAJE

DISCLAIMER: THIS IS A COMPUTER-GENERATED REPORT AND DOES NOT REQUIRE A PHYSICAL SIGNATURE.

Regd.Office: Shelton Sapphire, 8TH Floor, 806-B, Plot No: 18-19, Sector-15,  
CBD Belapur, Navi Mumbai-400614, Maharashtra. India.  
L—022-27582828, Website-www.shieldlubricants.com