



**Shield Lubricants & Specialities Pvt. Ltd.**

## **LABORATORY TEST REPORT**

PRODUCT NAME. : PRO GEAR EP 140 API GL-4	DATE : 22/02/2026
BATCH NO. : SL/26-02/2313	LAB.SR.NO. : 1472

SR. NO.	TEST	TEST METHOD	UNIT	SPECIFICATION	BATCH TEST REPORT
1	Appearance	Visual	....	Clear & Bright	Clear & Bright
2	Crackle Test	Visual	....	Nil	Nil
3	Colour	ASTM D-1500	....	L4.0 Max.	L3.0
4	Density @29.5°C	ASTM D-1298	Kg/ml	Report	0.8873
5	Kinematic Viscosity @ 100°C	ASTM D-445	cSt	27 Min. - 31 Max.	29.16
6	Kinematic Viscosity @ 40°C	ASTM D-445	cSt	Report	396.0
7	Viscosity Index	ASTM D-2270	....	Report	102
8	TAN, mg of KOH/gm	ASTM D-974	mg of KOH/gm	Report	0.52
9	Flash Point , COC	ASTM D-92	°C	220 Min.	240
10	Pour Point	ASTM D-97	°C	-9 Max.	-12

REMARK – SAMPLE PASS

PREPARED BY: ANIL JARHAD

APPROVED BY: SANDIP BHAYAJE

DISCLAIMER: THIS IS A COMPUTER-GENERATED REPORT AND DOES NOT REQUIRE A PHYSICAL SIGNATURE.