



LABORATORY TEST REPORT

PRODUCT NAME : M CUT SUPER	DATE : 08/03/2026
BATCH NO. : SL/26-03/2382	LAB.SR.NO. – 1531

SR. NO.	TEST PARAMETER	TEST METHOD	SPECIFICATION	BLEND RESULT
1	Appearance	Visual	Clear & Bright	Clear & Bright
2	Crackle Test	In-House	NIL	Nil
3	Colour	ASTM D-1500	L4.0 Max.	L2.5
4	Density @29.5°C	ASTM D-1298	Report	0.8785
5	Kinematic Viscosity @ 100°C	ASTM D-445	Report	5.06
6	Kinematic Viscosity @ 40°C	ASTM D-445	28.80 Min. - 35.20 Max.	29.58
7	Viscosity Index	ASTM D-2270	90 Min.	96
8	Flash Point, °C, COC	ASTM D-92	180 Min.	180
9	Weld load test	IP239	400 Max.	400
10	Cu Corrosion,@100°C	ASTM D-130	4C Max.	4C

REMARK: SAMPLE PASS

TESTED BY: RAJANI MORE

APPROVED BY: SANDIP BHAYAJE