



LABORATORY TEST REPORT

PRODUCT.NAME: SHIELD CUT 12	DATE :07/03/2026
BATCH. NO: SL/26-03/2440	LAB.SR.NO. – 1412

SR.NO	TEST	TEST METHOD	UNIT	SPECIFICATION		BATCH TEST REPORT
				Min.	Max.	
1	Appearance	Visual	Clear & Bright		Clear & Bright
2	Crackle Test	Visual	NIL		Nil
3	Density @ 29.5°C	ASTM D 1298	Kg/ml	Report		0.8107
4	Colour D	ASTM D 1500		L0.5	L0.0
5	Kinematic Viscosity @ 100°C	ASTM D 445	cSt	Report		2.97
6	Kinematic Viscosity @ 40°C	ASTM D 445	cSt	9	14	11.01
7	Viscosity Index	ASTM D 2270	100		127
8	Flash Point, COC	ASTM D92	°C	150		190
9	Pour Point	ASTM D97	°C		-3	-24

REMARK – SAMPLE PASS

TESTED BY:RAJANI MORE

APPROVED BY: SANDIP BHAYAJE

DISCLAIMER: THIS IS A COMPUTER-GENERATED REPORT AND DOES NOT REQUIRE A PHYSICAL SIGNATURE.

Regd.Office: Shelton Sapphire, 8TH Floor, 806-B, Plot No: 18-19, Sector-15,
CBD Belapur, Navi Mumbai-400614, Maharashtra. India.
L—022-27582828, Website-www.shieldlubricants.com