



LABORATORY TEST REPORT

| | |
|---|-------------------|
| PRODUCT.NAME: SHIELD SPINDLE OIL EE 10 (OS) | DATE :25/03/2026 |
| BATCH. NO: SL/26-03/2545 | LAB.SR.NO. – 1412 |

| SR.NO | TEST | TEST METHOD | UNIT | SPECIFICATION | | BATCH TEST REPORT |
|-------|-----------------------------|-------------|-------|----------------|------|-------------------|
| | | | | Min. | Max. | |
| 1 | Appearance | Visual | | Clear & Bright | | Clear & Bright |
| 2 | Crackle Test | Visual | | NIL | | Nil |
| 3 | Density @ 29.5°C | ASTM D 1298 | Kg/ml | Report | | 0.8107 |
| 4 | Colour D | ASTM D 1500 | | | L0.5 | L0.0 |
| 5 | Kinematic Viscosity @ 100°C | ASTM D 445 | cSt | Report | | 2.97 |
| 6 | Kinematic Viscosity @ 40°C | ASTM D 445 | cSt | 9 | 14 | 11.01 |
| 7 | Viscosity Index | ASTM D 2270 | | 100 | | 127 |
| 8 | Flash Point, COC | ASTM D92 | °C | 150 | | 190 |
| 9 | Pour Point | ASTM D97 | °C | | -3 | -24 |

REMARK – SAMPLE PASS

TESTED BY: RAJANI MORE

APPROVED BY: SANDIP BHAYAJE