



**LABORATORY TEST REPORT**

PRODUCT NAME :SHIELD PERFORMANCE DRIVE 4T 20W40 API SN	DATE : 22/04/2026
BATCH NO : SL/26-04/112	LAB.SR.NO. – 84

SR. NO.	TEST	TEST METHOD	UNIT	SPECIFICATION	BATCH TEST REPORT
1	Appearance	Visual	....	Clear & Bright	Clear & Bright
2	Crackle Test	Visual	....	Nil	Nil
3	Colour	ASTM D-1500	....	L3.0 Max.	L2.0
4	Density @29.5°C	ASTM D-1298	Kg/ml	Report	0.8624
5	Kinematic Viscosity @ 100°C	ASTM D-445	cSt	14.00 Min. - 15.50 Max.	14.33
6	Kinematic Viscosity @ 40°C	ASTM D-445	cSt	Report	118.8
7	Viscosity Index	ASTM D-2270	....	110 Min.	121
8	TBN, mg of KOH/gm	ASTM D-2896	mg of KOH/gm	7.3 Min.	7.89
9	Pour Point	ASTM D97	°C	-24 Max.	-27
10	Flash Point, COC	ASTM D92	°C	210 Min.	234

REMARK: SAMPLE PASS

TESTED BY: RAJANI MORE

APPROVED BY: SANDIP BHAYAJE

DISCLAIMER: THIS IS A COMPUTER-GENERATED REPORT AND DOES NOT REQUIRE A PHYSICAL SIGNATURE.